

**STUDY OF MECHANICAL AND PHYSICAL  
PROPERTIES OF NITRILE BUTADIENE RUBBER  
GLOVE WITH SULFUR, ACCELERATOR AND  
PARTICLE SIZE OF THE DISPERSION**

A dissertation submitted to the  
Faculty of Animal Science and Export Agriculture  
Uva Wellassa University  
In partial fulfillment of the requirements for the award of  
Bachelor of Science in Palm and Latex Technology and Value Addition

By

**EDINADURA DHANUSHI MALHARI MENDIS**

**Palm and Latex Technology and Value Addition Degree**

**Programme**

**Department of Export Agriculture**

**Faculty of Animal Science and Export Agriculture**

**Uva Wellassa University of Sri Lanka**

**2019**

## ABSTRACT

Sludge formation in the latex dipping tanks is the most destructive matter in the glove industry. This problem can cause quality defects of the glove and hence, high cost of production. This study was carried out to reduce the sludge quantity while improving the physical properties of the nitrile butadiene rubber glove by reducing the particle size of the dispersion. Particle size of the dispersion was reduced by increasing milling cycles in the pearl mill. Two milling cycles were considered in this study. Particle sizes of two samples were 2.5 $\mu\text{m}$  and 1 $\mu\text{m}$  according to the Dynamic Light Scattering test. Those dispersion samples were used to prepare compounds to measure the sludge quantity and gloves were prepared to investigate the physical properties. Particle size with the milling cycles were studied as a preliminary study. Further improvements of the physical properties of the glove were investigated using different sulfur/accelerator ratios in three sulfur vulcanizing systems. Two levels of sulfur/accelerator ratios in each system were used to determine a best ratio with better properties. Dispersion with 1  $\mu\text{m}$  particle size was given least sludge quantity than the dispersion with 2.5 $\mu\text{m}$  particle size while improving the properties. 3.5/1 sulfur/accelerator ratio was given better properties than the 2.5/0.5, 0.4/0.5, 0.8/3, 1/1, 1.5/1.5 ratios. Standard property levels in nitrile butadiene glove were considered as the control in this study. 1 $\mu\text{m}$  dispersion was given least sludge quantity with considerable improvement in physical properties. 3.5/1 ratio was given better properties than the 2.5/0.5, 0.4/0.5, 0.8/3, 1/1, 1.5/1.5 ratios. This is because vulcanizate with high promotion of polysulfidic bonds obtained high mechanical strength. Therefore, it is effective to use dispersions made from 1 $\mu\text{m}$  particle size with 3.5/1 sulfur/ accelerator ratio in the production of nitrile glove.

**Keywords:** particle size, physical properties, sludge, sulfur/accelerator ratio