

**DEVELOPMENT OF AN EDIBLE FILM USING  
COCONUT PROTEIN ISOLATE**

A dissertation submitted to the  
Faculty of Animal Science and Export Agriculture

Uva Wellassa University

In partial fulfilment of the requirements for the award of  
Bachelor of Science in Palm & Latex Technology and Value Addition

**By**

**JAYASINGHE MUDIYANSELAGE MADARA SASIRI  
JAYASINGHE**

**Palm & Latex Technology and Value Addition Degree Program**

**Faculty of Animal Science and Export Agriculture**

**Uva Wellassa University of Sri Lanka**

**2018**

## ABSTRACT

Most of food products are covered by a packaging to separate it from surrounding environment. There are several investigations on food packaging have shown that film forming ability of different plant proteins such as soy protein, mung bean protein, cowpea protein etc. This research was conducted to develop an edible film using coconut protein isolate from defatted coconut flour as an alternative for petroleum-based packaging materials. Coconut protein (CP) was isolated from the defatted coconut flour by alkaline extraction method. Extracted protein was dried using freeze drying and sieved through 800  $\mu\text{m}$  mesh. Percentage of protein of the extracted powder was analysed by kjeldahl digestion method. Four different combinations of corn starch (CS) (3%, 2%, 1% and 0%) and CP (0%, 1%, 2% and 3%) were used for film fabrication with two levels of pH (8.5 and 9.5) and two levels (2% and 0%) of polyethylene glycol (PEG) plasticizer. Casting technique was used for film preparation with 2% (w/v) constant glycerol level and distilled water. The experiment was arranged as a three-factor factorial design with three replicates. Physical, chemical and optical quality characteristics (moisture%, swelling index, solubility, thickness, light transmission%) of edible films were evaluated. Data was analyzed by ANOVA ( $p < 0.05$ ) using MINITAB16 software package. Results showed that, extracted CP has 78.43% of protein content. Combination of CS and CP were showed weaker film characteristics than pure treatments. CP films with 2.5% of PEG showed significantly ( $p < 0.05$ ) high moisture content ( $49.20\% \pm 0.43$ ), swelling index ( $483.96\% \pm 13.79$ ) at 8.5 pH and significantly high solubility ( $76.0\% \pm 1.4$ ) and thickness ( $0.33 \pm 0.01$  mm) at 9.5 pH. The pure CS film (pH 8.5 and 0% PEG) was showed significantly higher percentage of light transmission at 200 to 800 nm. In conclusion, the film prepared using 3% CP under pH 9.5 without addition of PEG exhibited overall better properties and CP can be effectively utilized as an edible food packaging material.

*Keywords:* Coconut protein isolate, Corn starch, Edible film, Polyethylene glycol